

# TOUGH MULTI-FILLER

FIBAREX

## FILLING, REPAIRING & LOCALISED SKIMMING

- ◆ REINFORCED WITH FIBRES FOR EXTRA STRENGTH
- ◆ TOUGH, WITH EXCELLENT ADHESION
- ◆ EASY TO SAND
- ◆ NO NEED TO SEAL THE SUBSTRATE \*



### PURPOSE

Exterior fibre-reinforced filler. Tough with excellent adhesion and versatile: for repairs, filling and skimming on all building substrates.

### SUBSTRATES

Tough Multi-Filler can be applied to either new or renovated substrates, unpainted or painted:

- Plaster and lime mortar, cement, concrete, old painted surfaces (except flexible covering)
- Breeze blocks, bricks, stone, glass and glazed tiles.

### OVERCOATING

Tough Multi-Filler can be overcoated with any type of filler, paint or wall coating. Do not coat directly with polyurethane paints nor epoxy solvent based paints.

### Physical and technical FEATURES

- Tough Multi-Filler: is a filler in powder form for exterior use, made with cement, selected mineral extracts, binders and fibres.
- Characterization (NFT 36-005): Family IV class 4c.
- Codification (EN 16-566):  $G_3S_2V_1W_1A_0C_0R_0$ .
- Mixing rate: add 400ml water per 1kg powder (40%).
- Application thickness: no depth limit.
- Capacity: 1.1 kg covers 1m<sup>2</sup> at 1mm depth.
- Working time: 40 minutes.
- Setting time: second coat as soon as the filler is hard and dry to the touch.
- Overcoating: can be painted in 24 hours average time (after complete drying).
- Color: white.
- Adhesion: filler/substrate (EN 16-566): > 0.8 Mpa.

### USE AND STORAGE CONDITIONS

- Application tools: filling knife, trowel or blade.
- Tool cleaning: after use, product residue can be rubbed off tools when dry (water cleaning is not necessary).
- Preservation: product guaranteed 6 months. Stored away from humidity. If found to be faulty within the guarantee period, we will arrange a replacement on proof of purchase.

### PACKAGING

Box: 2kg.  
Bag: 5kg and 10kg.

### RECOMMENDATIONS and care for use

The times mentioned are indicative and depend on the substrate, coat thickness, and the ambient conditions. Do not apply at a temperature below 5°C or above 35°C nor at a relative humidity over 80%.

### SUBSTRATES PREPARATION

Substrates to be prepared as per the current trade practices. \*Substrates must be hard, cohesive, clean, sound and dry.

### NORMATIVE DOCUMENTS to be referred to

- BS EN 16566:2014 (Paints and varnishes. Fillers for internal and/or external works).
- NF Environment – Paint fillers (NF446).

### HEALTH AND SAFETY

It is recommended to wear gloves and glasses while applying Tough Multi-Filler. Always wear a dust mask when sanding. Dispose of unused product and packaging responsibly at your local waste collection centre.

Safety data sheet available at [www.toupret.co.uk](http://www.toupret.co.uk)

UFI: STYV-FKNA-4RHR-XTH2

Contains cement – please read the care for use guidelines on the packaging or on the MSDS before handling.

The data sheet information, especially the guidelines relevant to the application and final use of the product are provided in good faith and result from TOUPRET's experience and knowledge of the products. The product should be used as per the trade practices rules book and in reference to our recommendations. The information provided is relevant to applications processed at a temperature of 20°C, a relative humidity of 50% and on average absorbency substrates. The times mentioned are only indicative and depend on the substrate, the coat thickness, and the ambient conditions.